

Media Certification for HP Latex

Evaluation Report



Vendor Name*

Metamark

Certification Number

July 19, 2018 - 35302

Date of evaluation

2018-07-19

Qualification

PASS

Platform

Latex 300-series

Certification Center

Color Concepts Netherlands

Substrate Information

Substrate Name

MD-X-100

Lot Number

N.A.

Substrate Type

Self Adhesive Vinyl

Substrate Sub Type

Cast

Thickness / Weight

50 micron

Profiling Process

Printer	Ink	RIP	Quality	Direction	Saturation
HP Latex 360	HP Latex 831	Any - RIP Independent -	10 pass	Bi	110%
Drying Temp.	Ink Limit	Vacuum	WUDTO	PMIN	
N.A.	N.A.	35	N.A.	N.A.	
Airflow	Curing Temp.	OMAS			
175	110C	N.A.			

Image Quality

Color Gamut	L*min	Area Fill Uniformity
494920	7.4	Average

Media Printer Interaction

Ink Transfer	Marks	Wrinkles	Dim. Stability	Rewetting
N.A.	Good	Good	-0.11	No

Image Handle Ability

Folding/Creasing	Scratchability	Dry Rub	Wet Rub	Cross Cut	Ink Adhesion	Ink Cracking
N.A.	4	Average	Good	N.A.	Good	N.A.

Ink Transfer	Waterfastness
N.A.	Water resistant

Overall Qualification

PASS

Comments

In conjunction with Color Concepts

HP's "Media Certification Program" ("Program") supplies information to media manufacturers, suppliers, and customers to assist in evaluating media compatibility with printers and inks from HP's Graphics Solutions Business. Media is supplied by independent third-party manufacturers. Inclusion in the Program and "Certified for" media shall not be construed as an endorsement by HP for any of the media or manufacturers. HP makes no representation or warranty of any kind for any media in the Program including but not limited to media availability, media quality, media performance, or manufacturer changes that may impact any media characteristics. The information contained herein is subject to change without notice. HP makes no representation as to the Program information's completeness or accuracy services are set forth in the express warranty statements accompanying such products and services. Nothing herein should be construed as constituting an additional warranty. HP shall not be liable for technical or editorial errors or omissions contained herein. This information is provided as a courtesy, free of charge, "AS-IS" by HP. HP MAKES NO EXPRESS OR IMPLIED WARRANTY OF ANY KIND REGARDING THIS INFORMATION. HP SHALL NOT BE LIABLE FOR ANY DIRECT, INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES, WHETHER BASED ON CONTRACT, TORT OR ANY OTHER LEGAL THEORY IN CONNECTION WITH OR ARISING OUT OF THE FURNISHING OR USE OF THIS INFORMATION.

